

# ExperFloor SL 13

COLOR OPTIONS: Grey

25

±%2 KG



## CEMENT BASED, SELF-LEVELING FLOOR SCREED (1-10 MM)

Cement based, self-leveling floor screed that can be applied up to 10 mm thickness.



SELF LEVELING



PROVIDES  
SMOOTH  
SURFACE

### TECHNICAL SPECIFICATIONS

Chemical Structure	Cement based powder containing high alumina plasticizer additives
Density	1,35 g/cm <sup>3</sup> (±0,1)
Mortar Density	2,00 g/cm <sup>3</sup> (±0,1)
Mixture Ratio	5,75-6,25 lt water / 25 kg powder
Working Time	30 minutes
Walkability Duration	24 hours
Crusting Time	20 minutes
Compressive Strength	≥6 N/mm <sup>2</sup> 1 Day (EN 13892-2) ≥35 N/mm <sup>2</sup> 28 Days (EN 13892-2)
Bending Strength	≥2 N/mm <sup>2</sup> 1 Day (EN 13892-2) ≥7 N/mm <sup>2</sup> 28 Days (EN 13892-2)
Bond Strength	≥1 N/mm <sup>2</sup>
Full Curing Time	28 days
Consumption	1,60-1,80 kg/m <sup>2</sup> (for 1 mm application thickness)

\* Tüm teknik değerler +23°C'de ve %50 bağıl neme göre hesap edilmiştir. Sıcaklık ve nem oranı değişimleri teknik değerleri değiştirmektedir.

### ADVANTAGES

- Easy to apply.
- Has self-leveling feature.
- Provides a smooth surface.
- It does not crack and swell.
- Resistant to abrasion and dusting.
- Suitable for underfloor heating systems.
- Can be applied with machine.

### APPLICATION AREAS

Used to create a smooth and shrinkage-free floor with high surface quality:

- Indoors and outdoors,
- In areas exposed to heavy pedestrian traffic such as residences, hospitals, educational buildings, shops,
- Underfloor heating,
- Before floor coverings such as carpet, parquet, PVC, linoleum, ceramic, marble, granite, epoxy on cement-based screed surfaces, concrete slab surfaces.

### SURFACE AND APPLICATION CONDITIONS

- The floor concrete must be cured and the moisture content of the concrete must not exceed 4%.
- Air temperature should be between +5°C and +35°C during application.

## Floor Systems

13813  
104225

GÜVEN MADENCİLİK İNŞAAT SAN. ve TİC. A.Ş.

# ExperFloor SL 13

COLOR OPTIONS: Grey

25

±%2 KG



## Floor Systems

13813  
104225

GÜVEN MADENCİLİK İNŞAAT SAN. ve TİC. A.Ş.

### SURFACE PREPARATION

- The application surface must be dry. It should be cleaned from dust, dirt, paint, oil and similar substances that will reduce adherence. Eyelet gaps should be filled. Oil-soaked surfaces should be cleaned with chemical cleaning agents.
- Material such as mortar and cement residues should be scraped off.
- Repair of surface damages with a depth of more than 2 cm should be filled with repair mortar 24 hours before application.
- The surface must be primed with ExperPrime AS 30 primer after surface preparation.
- Before application, areas such as wall edges and door fronts should be covered with profiles or tapes.

### PREPARATION OF MIXTURE

- Using a scale, pour 5,75-6,25 liters of clean water into a clean mixing bowl.
- Slowly add ExperFloor SL 13 into the water tank and mix with a low speed mixer for 3-5 minutes until a homogeneous and lump free mixture is obtained.
- The mixture is allowed to rest for approximately 1-2 minutes, then mixed again for 30 seconds and made ready for application.

### APPLICATION DETAILS

- Depending on the ground and weather conditions, ExperFloor SL 13 can be applied at least 30 minutes after primer application.
- The prepared mortar of a flowing consistency is poured onto the surface.
- If necessary, the thickness can be adjusted with a notched trowel to facilitate the spreading process.
- After spreading the product on the surface, air bubbles in the product should be eliminated by using a spiked roller and spiked shoes.
- In applications made with a mixer pump, the width of the application area should not exceed 6 meters in order not to disturb the spread of the material together.
- Continuous application is required to prevent the formation of cold joints in large areas.

### WARNINGS

- Do not apply in weather conditions below +5°C, above +30°C, in rainy and/or windy weather.
- Avoid application in areas that are frozen, in areas with the risk of freezing within 24 hours, in conditions that may prevent the application or that may damage the surface after application.
- Dilatation joints must be observed in the application area, if any.
- Profiles suitable for the thickness of the topcoat to be applied should be used.
- After application, wait at least 3 days before coating the surface.
- Do not apply on wet surfaces exposed to moisture.
- In areas with underfloor heating, the heating system should be turned off 24 hours before the leveling screed application and turned on 72 hours after the application.

### CONSUMPTION

- 1,60-1,80 kg/m<sup>2</sup> (for 1 mm application thickness)

### EQUIPMENT CLEANING

- Equipment should be cleaned with solvent immediately after use. Cured material can only be cleaned by mechanical means.

### STORAGE AND SHELF LIFE

- Should be stored in its unopened original packaging, in a closed, moisture-free, dry environment, protected from frost. Products should not be overloaded in a way to damage their packaging.
- Shelf life under appropriate storage conditions is 12 months from the date of production.

# ExperFloor SL 13

COLOR OPTIONS: Grey

25

±%2 KG



## Floor Systems

13813  
104225

GÜVEN MADENCİLİK İNŞAAT SAN. ve TİC. A.Ş.

### SAFETY PRECAUTIONS

- During use and storage, work clothes, protective gloves and masks should be used in accordance with the rules of Occupational and Labor Health. Eye, mouth and skin contact should be avoided and the contact area should be washed with plenty of water.
- In more dangerous situations or in case of ingestion of the product, a specialist doctor should be consulted immediately. Food and beverages should not be brought into the application areas. Keep out of the reach of children. For detailed information, the Safety Data Sheet (SDS) should be consulted.

### PRODUCT LIABILITY

- Güven Madencilik İnş. San. ve Tic. A.Ş., is only responsible for the quality of EXPERAS branded products. All data presented are the result of practical and scientific studies. The manufacturer cannot be held responsible except for the use of the correct products in appropriate areas and conditions.

### LEGAL NOTES

- The information and recommendations for the use of EXPERAS branded products are provided in good faith based on technical knowledge and experience, provided that they are maintained and handled under normal conditions and in accordance with the recommendations. Along with the products, the areas of use and surfaces may vary widely. It is necessary to ensure that the correct EXPERAS branded products are applied on appropriate surfaces and under appropriate conditions. In addition, all information and instructions regarding commercial factors and technical conformity must be strictly followed. The manufacturer cannot be held responsible for any damages and problems that may occur if not complied with. The applicator/user is obliged to make the relevant checks to ensure these details. The specifications of EXPERAS branded products may be changed when necessary. The property rights of third parties must be respected. When the order is confirmed, all existing technical conditions are essential for sales and transportation.

### REFERENCE STANDARDS

- TS EN 13813

